

Patented roller. Through different peripheral speeds, this roller is capable to align the advancement of the tiles inside the kiln, before the material reaches the firing zone.

Mineralogical composition

- Corundum
- Mullite
- Zirconium

Al ₂ O ₃ content	78%
Bulk density	2.85 Kg/dm ³
Apparent porosity	16%
Water absorption	5.8%
M.O.E. 20 °C	> 105 GPa
Thermal expansion	5.1*10 ⁻⁶ K ⁻¹



Identification color



Grey window
RAL 7040